

WHAT IS CLAIMED IS

1. Inserting paper for glass-like sheet materials comprised of a nonwoven sheet made of cellulose, wherein a content of hot water solubles in said nonwoven sheet is less than 0.1 wt%.

2. Inserting paper for glass-like sheet materials as set forth in claim 1, wherein said nonwoven sheet is formed without using a binder.

3. Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein said nonwoven sheet is pressed by a flat roller.

4. Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein said nonwoven sheet is supercalendered.

5. Inserting paper for glass-like sheet materials as set forth in claim 3, wherein said nonwoven sheet is supercalendered.

6. Inserting paper for glass-like sheet materials as set forth in claim 1 or 2, wherein a surface roughness of said nonwoven sheet is not more than 1.5  $\mu\text{m}$  as measured by a KES-FB-4S surface tester.

7. Inserting paper for glass-like sheet materials as set forth in claim 3, wherein a surface roughness of said nonwoven sheet is not more than 1.5  $\mu\text{m}$  as measured by a KES-FB-4S surface tester.

8. Inserting paper for glass-like sheet materials as set forth in claim 4, wherein a surface roughness of said nonwoven sheet is not more than 1.5  $\mu\text{m}$  as measured by a KES-FB-4S surface tester.

9. Inserting paper for glass-like sheet materials as set forth in claim 5, wherein a surface roughness of said nonwoven sheet is not more than 1.5  $\mu\text{m}$  as measured by a KES-FB-4S surface tester.